

SHIELD SPG 151M

High Range, Water-Reducing and Retarding Superplasticizer for Concrete



MICSHIELD®

Description

Shield SPG 151M is a highly effective liquid superplasticizer, used in the production of free-flowing concrete, self-compacting concrete, or as a water-reducing agent to promote ultimate strength, and suitable for use in hot and humid climatic conditions.

Uses

- Production of high strength concrete.
- Production of pumpable concrete.
- Production of pre-stressed concrete.
- Production of water impermeable concrete.
- For exposed concrete.

Characteristics / Advantages

- Retards the setting time of concrete.
- Contributes to better hydration of cement.
- Facilitates compaction of concrete.
- Reduces segregation and significantly improves workability and pumpability.
- Reduces shrinkage during setting or (crack prevention).
- Improves water impermeability.
- Compatible with all types of Portland cement.
- Free of chlorides and other corrosive ingredients.

Standard Compliance

- ASTM C494/C494M: Type G
- EN 934-2: Tables 11.1 and 11.2

Typical Properties

Appearance / Color	Dark brown liquid
Specific Gravity @ 23°C	1.15 ± 0.02
Freezing Point	0°C
Chloride Content (EN 480-10)	Nil
Nitrate Content	Nil

Application Instructions

1. Direction of Use

Shield SPG 151M should be added into the gauging water of the concrete mix, or into the ready-mixed concrete at site, just before discharge. In this case, the concrete truck mixer should rotate additionally for 3 minutes, to achieve uniform dispersion of the admixture into the concrete mass.

2. Dosage

0.5 – 2.8% by weight of cement and supplementary cementitious materials.

It is always recommended to carry out trial mixes, since the exact dosage rates depend on many factors such as required slump, quality of cement and aggregates, water/cement ratio, ambient temperature etc.

- An excessive dosage may cause retardation of setting time, without negatively affecting the final strength of concrete.
- Never add **Shield SPG 151M** to dry cement or dry aggregates.
- It must be considered that a low water/cement ratio increases the water impermeability of concrete.



3. Dispensing

Shield SPG 151M is best dispensed into the mixer via automated dosing equipment as part of the batching process or, alternatively, added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant.

Shield SPG 151M is suitable for use with all types of Portland cement (OPC and SRC) and cement blends with supplementary cementitious materials such as GGBS, PFA, and micro-silica.

4. Concrete Placement and Curing

When using **Shield SPG 151M** in concrete, it is important to observe the rules for best-demonstrated concreting practices in production, placing, and curing. ACI Manual of Concrete Practice can provide valuable guidance.

Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Apply a curing compound or use wet hessian and polythene.

5. Cleaning

Collect and dispose of spillage. Do not discharge into drains or watercourses or onto the ground. Soak up with an inert absorbent or container and remove in the best available method.

Shelf Life and Storage

Shield SPG 151M has a shelf life of 12 months when stored in its original unopened packaging in cool and dry conditions, protected from direct sunlight, heat, and moisture. Shelf life may be reduced if the recommended storage conditions are not followed.

Packaging

Shield SPG 151M is supplied in 1000-liter tanks. Bulk delivery on request.

Safety Instructions

Refer to the most recent Material Safety Data Sheet for information and advice on the safe handling, storage and disposal of the product.

Limitations

- The mix design must be proportioned for the local materials used and trial mixes performed to verify admixture dosage to give the required concrete properties.
- If frozen and/or if precipitation has occurred, only use the admixture after it has been totally thawed and mixed.
- Do not add directly onto dry cement or aggregates.
- When using high-workability concrete, take special care that formwork is properly installed and secured.
- If the setting time of the concrete is extended, ensure proper curing. In this case, other properties may not be affected, and a higher ultimate strength can be achieved.
- Check compatibility when using with other admixtures.

Technical Support

Refer to technical information, method statement, or contact technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600
Fax. +962 6 5833890

Email: info.shield@manaseer-ic.com
Website: www.manaseergroup.com

LEGAL DISCLAIMER: All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.

Version 230615 SP-AF -151M-001

Manaseer Industrial Complex