

Shieldcoat EIFS



Polymer-modified, Cement-based Render and Base Coat for Thermal Insulation Boards

Description

Shieldcoat EIFS is an easy-to-use, polymer-modified, cement-based mortar and base coat, supplied as a ready-to-use blend of dry powders, and only requires the addition of clean water. **Shieldcoat EIFS** is designed to be used as a base coat on thermal insulation boards.

Uses

- Render for thermal insulation boards.
- Indoor and outdoor situations.
- For walls and ceilings.
- Vertical, horizontal, and overhead applications.

Characteristics / Advantages

- Factory-controlled, pre-blended dry mix, only requires the addition of clean water.
- Excellent adhesion strength.
- Easy to apply.
- Water and frost resistant.
- Non-flammable.

Packaging

Shieldcoat EIFS is supplied in 25 kg bags.

Shelf Life and Storage

Shieldcoat EIFS has a shelf life of 12 months when stored in its original unopened packaging in cool and dry conditions, protected from direct sunlight, heat, and moisture. Shelf life may be reduced if the recommended storage conditions are not followed.

Safety Instructions

Like any cement-based product, **Shieldcoat EIFS** contains hydraulic cement and may cause irritation to the skin or eyes. For further information Refer to the Material Safety Data Sheet.

Typical Properties

Color	Grey
Appearance	Powder
Mixed Density (@ 23°C)	1.55 ± 0.10 g/ml
Working Time (@ 23°C)	1 hour
Compressive Strength (BS EN 1015-11) @28 days	≥ 10.0 MPa
Flexural Strength (BS EN 1015-11) @28 days	≥ 2.0 MPa
Application Thickness	2 – 6 mm
Yield / 25 kg bag	19.5 Liters, covers 4 m ² / 5 mm thickness

Technical information corresponds to the data, which were obtained at (23 ± 2 °C) temperature and (50 ± 5%) relative humidity.

Application Instructions

1. Substrate Temperature

+5°C to +40°C

2. Surface Preparation

The application substrate and insulation boards must be free from dust, loose material, surface contamination, and materials that may reduce bond or prevent adhesion.

Insulation boards must be firmly anchored in place. Any gaps between boards must be filled with foam or the same material and any surface irregularities larger than 2 mm must be sanded flush.

Allow 24 – 48 hours to pass after the adhesion of insulation boards before applying **Shieldcoat EIFS**, depending on weather conditions.

3. Mixing

Shieldcoat EIFS requires 5.0 – 6.0 Liters of potable water per 25 kg bag, depending on the desired consistency. For optimum results, mixing should be performed using a forced-action high-shear mixing paddle, powered by a heavy-duty electric mixing drill.

Add the pre-measured amount of water to a clean mixing bucket. Add **Shieldcoat EIFS** powder slowly to the water whilst mixing and continue mixing for 3 – 5 minutes until a smooth, homogenous, lump-free consistency is achieved. Allow this mixture to stand for 3 – 5 minutes and then re-mix for another 1 – 2 minutes prior to use.

4. Application

Apply a 2 – 3 mm thick layer of the mixed **Shieldcoat EIFS** to the affixed insulation board using a steel trowel to the entire surface of the insulation board.

Fully embed the reinforcing mesh in the wet base coat troweling from the center to the edge of the reinforcing mesh to avoid wrinkles. The reinforcing mesh shall be overlapped 100 mm at all joints and turned at least 200 mm at all corners, windows, and door openings.

The overall minimum base coat thickness shall be sufficient to fully embed and encapsulate the reinforcing mesh so that it is no longer visible. It is recommended to apply a second coat within 24 hours of the first coat, dependent on temperature and weather conditions. The total thickness of two coats must be 4 – 6 mm to ensure that the fiberglass mesh is well encapsulated in the base coat layer.

5. Cleaning

All mixing equipment and application tools should be cleaned immediately with clean water. Hardened material should be mechanically removed.

6. Curing

Curing is not normally necessary, but freshly applied material should be protected from rain and strong drying winds.

7. Overcoating

Finishes such as paints or stucco may be applied after the material has dried for 2 – 3 days depending on the weather conditions. Follow the application instructions for the overcoat material regarding any surface preparation, application, etc.

Consumption and Coverage (For 25 kg bags)

Yield: ~ 19.5 Liters

Consumption: 1.25 – 1.30 kg/m²/mm thickness.

Coverage: 19 – 20 m²/25 kg bag/mm thickness

Limitations

- Do not apply the product if the ambient temperature is less than 5°C.
- Hot weather practices should be adopted during application and curing if the temperature is above 35°C. In hot conditions, store the material in a cool environment prior to mixing and use chilled mixing water.
- If time exceeded 24 hours before applying the second coat, the surface must be saturated with water prior to application.

Technical Support

Refer to technical information, method statement, or contact technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600
Fax. +962 6 5833890

Email: info.shield@manaseer-ic.com
Website: www.manaseergroup.com

LEGAL DISCLAIMER: All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.

Version 250209 SP-AF –Shieldcoat EIFS -003