

Shieldputty G10

Cement-based, Putty and Skim Coat



Description

Shieldputty G10 is an easy-to-use, economical, cement-based grey putty and skim coat, ready to use as a pre-packed dry powder that only requires the addition of clean water on site. **Shieldputty G10** is suitable for internal applications.

Uses

- Wet and dry conditions.
- Indoor applications.
- Vertical and overhead applications.
- Fine crack filler.
- To give a smooth surface to many substrates such as:
 - Repaired concrete
 - Concrete blocks and panels
 - Aerated lightweight blocks
 - Bricks
 - Precast concrete walls and ceilings

Characteristics / Advantages

- No primer is needed.
- Excellent adhesion to many substrates.
- Creamy consistency with easy application.
- Provides very smooth surface finishes.
- Self-cured.
- Shrinkage-compensated.
- Low permeability
- Easy to be sanded.
- Applied surface can be painted after 72 h.

Standard Compliance

BS EN 998-1: 2010 Class CS IV

Packaging

Shieldputty G10 is supplied in 20 kg bags.

Shelf Life and Storage

Shieldputty G10 has a shelf life of 12 months when stored in its original unopened packaging in cool and dry conditions, protected from direct sunlight, heat, and moisture. Shelf life may be reduced if the recommended storage conditions are not followed.

Typical Properties

Appearance/ Color	Grey powder
Specific Gravity (@ 23°C)	1.60 ± 0.10 g/ml
Open Time	~ 60 minutes
Maximum Aggregate Size	60 µm
Yield / 20 kg bag	16.5 Liters
Application Thickness / Coat	1 – 2 mm
Overcoating Time	3 hours
Setting Time (BS EN 196-3)	8 – 9 hours
Compressive Strength (BS EN 1015-11) @28 days	≥ 8.0 MPa
Flexural Strength (BS EN 1015-11) @28 days	≥ 1.0 MPa
Bond Strength (BS EN 1015-12) @28 days	≥ 0.50 MPa

Application Instructions

1. Substrate Temperature

+5°C to +35°C

2. Surface Preparation

The substrate must be free from dust, loose materials, surface contamination, and any materials that may reduce bond or prevent adhesion of the putty. Surface laitance should be removed by light scabbling or grit blasting to provide a roughened key for the putty.

Thoroughly dampen the surface of the concrete with clean water to provide a saturated surface dry condition (SSD). Poor-quality concrete may require soaking for a significant length of time. Any excess water shall be removed prior to application.

3. Mixing

Shieldputty G10 requires 6.5 – 7.0 liters of potable water per 20 kg bag. For optimum results, mixing should be performed using a forced-action high-shear mixing paddle, powered by a heavy-duty electric mixing drill. Add the pre-measured amount of water to a clean mixing bucket. Add the **Shieldputty G10** powder slowly to the water whilst mixing and continue mixing for 3 – 5 minutes until a smooth, homogenous, lump-free consistency is achieved.

4. Application

Apply the mixed material to the prepared surface using a steel float, trowel, or spatula to a thickness of 1 – 2 mm. Further coats, to increase thickness, may be applied after the waiting time has passed (3 hours minimum).

As the material sets, it can be troweled to a smooth surface using a steel float or, alternatively, finished with a sponge to give a textured finish.

5. Cleaning

All mixing equipment and application tools should be cleaned immediately with clean water. Hardened material should be mechanically removed.

6. Curing

Curing is not normally necessary, but freshly applied material should be protected from rain and strong drying winds.

Consumption and Coverage (For 20 kg packs)

Yield: 16.5 Liters

Consumption: 1.15 – 1.20 kg/m²/mm thickness.

Coverage: 16.5 – 17.5 m²/20 kg bag/mm thickness

Safety Instructions

Shieldputty G10 contains hydraulic cement and may cause irritation to skin or eyes. Refer to the most recent Material Safety Data Sheet for information and advice on the safe handling, storage, and disposal of the product.

Limitations

- Do not apply the product if the ambient temperature is less than 5°C.
- Surface may stain if excess water is used to finish the material.
- Not recommended to apply directly to painted surfaces.
- Hot weather practices should be adopted during application and curing if the temperature is above 35°C. In hot conditions, store the material in a cool environment prior to mixing and use chilled mixing water.

Technical Support

Refer to technical information, method statement, or contact technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600
Fax. +962 6 5833890

Email: info.shield@manaseer-ic.com
Website: www.manaseergroup.com

LEGAL DISCLAIMER: All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.

Version 240703 SP-AF –G10-007