

Shield GeoTex 150

Non-Woven Geotextile



MICSHIELD®

Description

Shield GeoTex 150 is polypropylene based, needle-punched, thermally-bonded nonwoven geotextile that forms a strong, dimensionally stable, and durable fabric. Designed to provide excellent separation, filtration, and protection performance for various geotechnical and civil engineering applications.

Uses

- Used as a filter, allowing water to pass while retaining soil particles.
- Used for soil stabilization in road, railway, basins and dams construction.
- Works as a moisture barrier when impregnated with asphalt or resin.
- Provides separation between different soil or aggregate layers.
- Serves as a drainage layer for water and gas movement within the soil.
- Applied in landfills, landscaping, and drainage systems as a separator and filter.
- Offers protection to waterproofing membranes and floors.

Characteristics / Advantages

- Lightweight and easy to handle, cut, and install on site.
- High permeability.
- Resistant to UV radiation and chemicals.
- High tensile strength.
- High elongation.
- Dimensional stability under stress.
- Flexibility and long durability.

Shelf Life and Storage

Shield GeoTex 150 has an unlimited shelf life when stored in cool and dry conditions, protected from direct sunlight, heat, and moisture. The storage area should be free from any equipment that generates ozone.

Properties

Color	White
Roll Width	3 or 6 m
Roll Length	200 m
Wight per unit area (EN ISO 9864)	150 g/m ²
Thickness @2 kPa (EN ISO-9863-1(A))	1.4 mm
Tensile Strength MD (EN ISO 10319)	12 kN/m
Tensile Strength CD (EN ISO 10319)	12 kN/m
Tensile Elongation MD (EN ISO 10319)	55%
Tensile Elongation CD (EN ISO 10319)	60%
Static Puncture Resistance (EN ISO 12236)	1900 N
Dynamic Perforation Resistance (EN ISO 13433)	30 mm
Characteristic Opening Size (EN ISO 12956)	80 microns
Water Permeability Normal to the plane 50mm WH (EN ISO 11058)	90 L/m ² /s
UV Resistance @ 500 h (EN 12224)	>70 %
Durability Oxidation Resistance (EN ISO 13438)	Up to 25 years

Technical Support

Refer to contacting technical information, method statement or technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600
Fax. +962 6 5833890

Email: info.shield@manaseer-ic.com
Website: www.manaseergroup.com

Version 251126-SP-FB –GeoTex150-001

LEGAL DISCLAIMER: All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.