

# Shieldcoat LM

## Acrylic Line Marking Paint for Tennis Courts



### Description

**Shieldcoat LM** is a ready-to-use acrylic paint, formulated as a line marking on sports surfaces. It enhances the longevity, UV stability, and visual appeal of flooring surfaces.

### Uses

- Tennis courts, walkways, recreational areas.
- Multi-sport facilities and halls.
- Playgrounds and running tracks.
- Fitness centers and outdoor courts.

### Typical Properties

|                          |              |
|--------------------------|--------------|
| Color / Appearance       | White liquid |
| Specific Gravity (23 °C) | 1.35 ± 0.1   |
| Touch Dry Time (25°C)    | 1 hour       |
| Overcoating Time (25°C)  | 2 hours      |

### Characteristics / Advantages

- Ready-to-use and easy to apply by roller, sprayer or brush.
- Resistant to UV and weathering conditions.
- Excellent adhesion strength with cement-based substrates and asphalt surfaces.
- Rapid drying characteristics.
- Water-resistant.
- Low VOC and environmentally friendly.
- Resistant to dirt pickup.

### Coverage

Approximately 2.5 – 4.5 m<sup>2</sup>/kg, but this may vary due to site wastage, substrate condition/profile, and porosity.

### Packaging

**Shieldcoat LM** is supplied in 25 kg buckets.

### Safety Instructions

Avoid contact with the eyes and skin. In case of direct contact with the skin, wash the affected area immediately with water for several minutes. If it comes into contact with the eyes, rinse immediately with lukewarm water for at least 15 minutes and get medical advice or treatment if any emergency warning signs appear. For further information, refer to the Material Safety Data Sheet.

### Shelf Life and Storage

**Shieldcoat LM** has a shelf life of 12 months when stored in its original unopened packaging in cool and dry conditions, protected from direct sunlight, heat, and moisture.

Shelf life may be reduced if the recommended storage conditions are not followed.

## Application Instructions

### 1. Surface Preparation and Priming

The substrate (layer of **Shieldcoat ProGuard S**) must be clean and free from dust, loose materials, surface contamination, and materials that may reduce bond or prevent adhesion. **Shieldcoat ProGuard S** must be allowed to cure for 48 hours prior to application.

### 2. Mixing

**Shieldcoat LM** should be thoroughly stirred prior to application to ensure a homogenous mixture.

### 3. Application

**Shieldcoat LM** is applied onto the textured coating layer (**Shieldcoat ProGuard S**) the next day using a roller. coverage.

### 4. Cleaning

All mixing and application equipment should be cleaned immediately with clean water. Hardened material should be mechanically removed.

### 5. Curing

Allow the coating to cure fully before exposure to moisture or traffic.

## Limitations

- Do not apply the product if the ambient temperature is less than 5°C.
- Hot weather practices should be adopted during application and curing if the temperature is above 35°C. In hot conditions, store the material in a cool environment prior to application.
- Ensure wearing appropriate personal protective equipment (PPE); gloves, eye protection, masks, and protective clothing, and ensure good ventilation during application.

## Technical Support

Refer to technical information, method statement, or technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302  
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600  
Fax. +962 6 5833890

Email: [info.shield@manaseer-ic.com](mailto:info.shield@manaseer-ic.com)  
Website: [www.manaseergroup.com](http://www.manaseergroup.com)

**LEGAL DISCLAIMER:** All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.

Version 260608 SP-FB – LM-001