

Shieldcoat M



Single-component, Trowel-applied, Acrylic-based Granular Textured Coating

Description

Shieldcoat M is a ready to use, trowel-applied, water-based decorative textured coating, formulated from high-quality acrylic binders, selected aggregates and additives to give a durable, elastic, granular finish similar to roughcast that covers minor cracks, defects, and surface undulations in substrates, available in a wide range of colors.

Uses

- Interior and exterior applications.
- Ideal to finish EIFS applications.
- Renovation/retrofit works.
- Suitable for various substrates such as concrete substrates, cement boards, plasters, renders, chipboards, and drywalls.

Characteristics / Advantages

- Easy to use and environmentally friendly.
- Flexible, with high resistance to impact and abrasion.
- Extremely tough, resistant to weather and UV conditions.
- Vapor permeable, allows breathability of the substrate.
- Non-toxic.

Shelf Life and Storage

Shieldcoat M has a shelf life of 12 months when stored in its original unopened packaging in cool and dry conditions, protected from direct sunlight, heat, and moisture.

Shelf life may be reduced if the recommended storage conditions are not followed.

Packaging

Shieldcoat M is supplied in 25 kg buckets.

Typical Properties

Appearance/ Color	Colored thick paste
Specific Gravity (23 °C)	1.70 ± 0.05
Maximum Aggregate Size	1.5 mm
Drying Time (23 °C)	3 – 5 hours
Full Cure	7 days

Application Instructions

1. Substrate Temperature

+5°C to +35°C

2. Surface Preparation

The substrate must be sound and free from dust, loose material, surface contamination, and materials that may reduce bond or prevent adhesion. Cracks, voids, and damage should be repaired using the appropriate product from the Manaseer ranges.

Protect adjacent areas that are not to be coated by suitable means. Apply **Shieldprime AC** to prime and seal prepared substrates prior to the application of **Shieldcoat M**.

3. Application

The container of **Shieldcoat M** should be stirred prior to use to ensure a homogenous mixture.

All adjacent surfaces not intended for coating should be masked and protected.

Apply **Shieldcoat M** onto the prepared and primed substrate with a steel trowel or Tyrolean at a 0.7 – 2.0 mm film thickness. Excess material must be removed before the finishing process.

Shieldcoat M can be diluted with water up to 5% if necessary.



4. Finishing

The desired scratch finish is achieved using a plastic float as below:

Vertical	: Float moved in vertical direction
Horizontal	: Float moved in horizontal direction
Random	: Float moved in circular motion
Cross-hatched	: Float moved in horizontal and vertical directions

5. Cleaning

All mixing equipment and application tools should be cleaned immediately with clean water. Hardened material should be mechanically removed.

6. Curing

Curing is not normally necessary, but freshly applied material should be protected from rain until fully dry to ensure optimum performance.

Consumption

Approximately 1.5 – 2.00 kg/m².

Consumption rate may vary due to site wastage and substrate condition / profile.

Safety Instructions

Avoid contact with the eyes and skin. In case of direct contact with the skin, wash the affected area immediately with water for several minutes. If it comes into contact with the eyes, rinse immediately with lukewarm water for at least 15 minutes and get medical advice or treatment if any emergency warning signs appear. For further information, refer to the Material Safety Data Sheet.

Technical Support

Refer to technical information, method statement, or contact technical support team for any inquiry.

Address: Manaseer Group, 8th Circle, King Abdullah II St. 302
P.O. Box 925988 Amman, 11110, Jordan

Phone +962 6 5800600
Fax. +962 6 5833890

Email: info.shield@manaseer-ic.com
Website: www.manaseergroup.com

LEGAL DISCLAIMER: All information provided, and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.

Version 260510 SP-FB -M-001

Manaseer Industrial Complex